



TG-A3200L

Low Bleed Thermal Pad

REACH Compliant

RoHS Compliant

UL Comparable

Features

- Low bleed
- High compressibility
- Self-adhesive
- High thermal conductivity


Applications:

Best for high power applications


Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

Properties



Thermal Conductivity : 3.2 W/m·K



Hardness : 35 (Shore OO)



Contact Pressure, Thermal Impedance, and Deflection



Properties	Unit	TG-A3200L	Tolerance	Test Method
Thermal Conductivity	W/m·K	3.2	±10%	ASTM D5470 Modified
Thickness	mm	0.5~8.0	-	ASTM D374
	inch	0.0197~0.3149	-	ASTM D374
Color	-	Light Gray	-	Colorimeter CIE 1976
Flame Rating	-	V-0	-	UL 94
Dielectric Breakdown Voltage	KV/mm	≥6	-	ASTM D149
Weight Loss	%	<1	-	ASTM E595 Modified
Density	g/cm³	3	±5%	ASTM D792
Operating Temperature	°C	-50~+150	-	-
Volume Resistivity	Ohm-m	10 ¹³	±10%	ASTM D257
Bleeding Width	mm	<3	-	T-Global Test Method
Tensile Strength @T3.0mm	kgf/cm²	≥20	-	ASTM D412
Elongation	%	≥120	-	ASTM D412
Standard Format	-	Sheet	-	-
Hardness	Shore OO	35	±10	ASTM D2240

※ For thicknesses less than 1.0mm, hardness will be adjusted to 50-75 Shore OO to facilitate effective removal of liner during production

※ Different tolerances according to the selected thickness

※ Die-cut for different shapes

T-Global USA LLC

2880 Zanker Road, Suite 103, San Jose, CA 95134, USA

T +1(669)345-0002 E usa@tglobalcorp.com W tglobal-usa.com

Version20
20250103



NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper do not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented with out guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.